

TECHNICAL DATA SHEET

General properties EN 655	Standard - Test Method	Unit	Specification
Dimensions	EN 427	mm	≤ 0.13% up to 0.5mm max
Squareness and straightness	EN 727	mm	≤ 0.25 ≤ 0.35
Overall thickness	EN 428	mm	± 0.20
Thickness of agglomerated composition cork base	EN 429	mm	2.5
Thickness of polyvinylchloride (average)	EN 429	mm	(0.25mm) ± 10%
Wear layer density	EN 436	kg m ³	Nominal value (1360) ± 50
Mass per unit area	EN 430	g m ²	Nominal value (2900) + 13%; -10%
Dimensional stability after exposure to heat	EN 434	%	≤ 0.4
Curling after exposure to heat	EN 434	mm	≤ 6
Peel resistance	EN 431	N 50mm	≥ 35